

TEST DATA

Theoretical Maximum Specific Gravity and Density of Bituminous Paving Mixtures

Technician: \_\_\_\_\_ Date: \_\_\_\_\_

Sample Description: \_\_\_\_\_

\_\_\_\_\_

Sample Identification No: \_\_\_\_\_

Testing Procedure:  AASHTO T 209

Item	Results
(A) Weight of Oven Dried Mix Sample in Air (g)	
(B) Weight of Pycnometer + Water at 25°C (g)	
(C) Weight of Pycnometer + Loose Mix + Water at 25°C (g)	
(D) Theoretical Maximum Specific Gravity $G_{mm} = A/(A+B-C)$	